

Solid Silicone Elastomer Sheeting

Grades

kSil™GP30 kSil™GP40 kSil™GP50
kSil™GP60 kSil™GP70 kSil™GP80

Temperature Range

-60°C (-76°F) to 230°C (446°F)
and up to 250°C (482°F) intermittent

Specifications

Our colour range has been tested and is in compliance with the American Food and Drugs Administration (FDA) 21 CFR 177-2600, BFR XV Empfehlung and colour bleed test according to BFR Empfehlung part B 11 & Directive EC 1935/2004.

Translucent, Blue, White, Red and Black have been approved by WRAS (Water Regulations Advisory Service) for use with potable water at temperatures up to 85°C (185°F). The listing number is 1310541.

These products meet the flammability requirements of FAR 25/JAR 25/CS 25 Appendix F, Part 1, (a)(1)(iv) and (a)(1)(v) horizontal flammability tests and Automotive Standard PART 571FMVSS302.

Environment Resistance

Silicone rubber products have an excellent resistance to ozone, oxidation, ultraviolet light, corona discharge, cosmic radiation, ionising radiation and weathering in general.

Availability

- Supplied in continuous roll lengths.
- Widths of 1200mm (standard), 1500mm and 1800mm.
- Pressure sensitive adhesive backing.
- Punched and Water Jet gaskets.
- Full range of standard colours.
- Capability to colour match.

Availability

Mouldings Sheeting Gaskets Cables
○ ● ● ○

Extrusions Compound Tubing
○ ○ ○

General Characteristics

Test	Result	Standard
Brittle Point	-80°C (-112 °F)	ASTM D746
Limiting Oxygen Index	24.0 %	BS 2782 Part 1
Thermal Conductivity	0.24 W.m ⁻¹ .K ⁻¹	VDE 0304
Radiation Resistance	>10 ⁵ Grays (10 ⁷ Rads) typical	
Dielectric Strength	23 kV.mm ⁻¹	VDE 0303
Dielectric Constant	2.9	VDE 0303
Dissipation Factor	3x10 ⁻⁴	VDE 0303
Volume Resistivity	3x10 ¹⁵ Ω.cm	VDE 0303

Typical Applications

Automotive, Domestic & Commercial
Catering, Construction, Electronics, Energy,
Food & Beverage, Heating and Ventilation
(HVAC), Industrial, Lighting, Marine

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.

Solid Silicone Elastomer Sheeting

Mechanical Properties

Property	Units	KSJTM GP30		KSJTM GP40		KSJTM GP50		KSJTM GP60		KSJTM GP70		KSJTM GP80		Test Method
		Typical Value	(1150)	Typical Value	(1300)	Typical Value	(1300)	Typical Value	(1450)	Typical Value	(1450)	Typical Value	(1015)	
Hardness	Shore A ± 5	30		40		50		60		70		80		ASTM D2240 DIN ISO 7619-1
Tensile Strength	MPa (psi)	8.0 (1150)		9.0 (1300)		9.0 (1300)		10.0 (1450)		10.0 (1450)		7.0 (1015)		ISO 37 type 1 ASTM D412 die C DIN 53504 type S1
Elongation to Failure	%	500		625		450		400		320		215		ISO 37 type 1 ASTM D412 die C DIN 53504 type S1
Tear Strength	N/mm (lb./in.)	16.0 (91)		23 (130)		18 (100)		22 (125)		20 (115)		17 (88.5)		ASTM D624 die B
Compression Set 24 hours @ 150°C	%	23		25		15		13		9		18		BS 903 pt A5 type B DIN/ISO 815 type B
Compression Set 22 hours @ 300°F	%	20		22		16		10		10		16		ASTM D595 method B type 2

Extra Information

In-house capabilities for extensive industry specific testing available on request.