

SILICONE HIGH STRENGTH

HARDNESS (H)	Sh.A3	DIN 53505	50±5
TENSILE STRENGTH (CR)	MPa	DIN 53504	9,4
MODUL at 300 %	MPa	DIN 53504	2,3
ELONGATION (AR)	%	DIN 53504	690
TEAR STRENGTH	N/mm	ASTM D 624B	40
SPECIFIC WEIGHT	g/cm ³	DIN 53479	1,16
Temperature min. and max.		-60 +260 °C	
.....			
.....			
.....			
.....			